



AMF THERMATEX® Feinstratos

- AMF THERMATEX® Feinstratos creates an even, uniform ceiling appearance due to its finely textured surface
- Good sound attenuation (34 dB)
- Good light reflectance (85%)
- Ideal for retail, meeting rooms, installation rooms or production areas



AMF THERMATEX® FEINSTRATOS

Edge details Additional edge details on request		Board 	Tegular 24 	Tegular 15 	Finesse 	SL2 	K2C2 	
Thickness (mm)		15	15	15	19	19	15	
Dimensions (mm) Additional sizes on request		600 x 600 625 x 625 1200 x 600 1250 x 625 1800 x 300 2500 x 300	600 x 600 625 x 625 1200 x 600	600 x 600 625 x 625 1200 x 600	600 x 600	2000 x 312,5 2500 x 312,5	2000 x 312,5 2500 x 312,5	
System		Exposed demountable - System C Exposed - Bandraster, demountable - System I.3 Exposed - Corridor, demountable - System F.3			Concealed, demountable - System A.2 / A.3	Semi-concealed planks, demountable - System I.3 Semi-concealed planks - Bandraster, demountable - System I.2 Semi-concealed planks - Corridor, demountable - System F.2	Semi-concealed planks, non-demountable - System I.3 Semi-concealed planks - Bandraster, non-demountable - System I.1 Semi-concealed planks - Corridor, non-demountable - System F.1	
Weight		3.8 - 5.0 kg / m ²						
Colour		White						
Sound absorption		EN ISO 354 $\alpha_w = 0.20$ as per EN ISO 11654 - Class E Frequency <i>f</i> (Hz) α_p						
			125	250	500	1000	2000	4000
			0.35	0.20	0.15	0.15	0.20	0.20
		NRC = 0.15 as per ASTM C 423						
Sound attenuation		EN ISO 10848-2 $D_{n,f,w} = 34$ dB (Board, Tegular 24, Tegular 15, K2C2) CAC = 35 dB (Board, Tegular 24, Tegular 15, K2C2)			$D_{n,f,w} = 38$ dB (Finesse, SL2) as per EN ISO 717-1 CAC = 38 dB (Finesse, SL2) as per ASTM E 413-10			
Sound reduction		EN ISO 10140-2 $R_w = 21$ dB as per EN ISO 717-1						
Fire reaction		Euroclass A2-s1, d0 as per EN 13501-1			RUS KM1 (G1, V1, D1, T1) as per 123-FZ			
Light reflectance		85%						
Thermal conductivity		$\lambda = 0.060$ W/mk as per EN 12667						
Humidity resistance		95% RH						
Indoor air quality		 A+	 E1	 IACG				
Cleanability								
Sustainability		 EN ISO 14021	 EN ISO 14025	 EC 1272/2008 Annex G				
		37-43%						

Products may vary from country to country. Please contact your local sales representative.
For further information and legal notice, please visit our website.